

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau**Rec'd PCT/PTO****10 SEP 2004**

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>C08G 65/26, C10L 1/18</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 98/44022</b> <b>(43) International Publication Date:</b> 8 October 1998 (08.10.98)
<b>(21) International Application Number:</b> PCT/EP98/01640 <b>(22) International Filing Date:</b> 20 March 1998 (20.03.98) <b>(30) Priority Data:</b> 03/832,167      2 April 1997 (02.04.97)      US <b>(71) Applicant (for all designated States except MN):</b> ARCO CHEMICAL TECHNOLOGY, L.P. [US/US]; Two Greenville Crossing, Suite 238, 4001 Kenneth Pike, Greenville, DE 19807 (US). <b>(71) Applicant (for MN only):</b> ARCO CHEMIE TECHNOLOGIE NEDERLAND B.V. [NL/NL]; Theemsweg 14, NL-3197 KM Botlek Rotterdam (NL). <b>(72) Inventors:</b> COMBS, George; 245 Donofrio Drive, Downing- town, PA 19335 (US). McDANIEL, Kenneth, G.; 1005 Pine Valley Circle, West Chester, PA 19382 (US). <b>(74) Agent:</b> SMAGGASGALE, Gillian, Helen; Mathys & Squire, 100 Gray's Inn Road, London WC1X 8AL (GB).		<b>(81) Designated States:</b> AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> POLYOXYALKYLENE MONOETHERS WITH REDUCED WATER AFFINITY  <b>(57) Abstract</b>  Oleophilic polyoxyalkylene monoethers having reduced water affinity are disclosed. The monoethers have a hydrocarbyl residue, a polyoxyalkylene moiety, and a hydroxyl end group. The monoethers contain less than about 6 mole percent of alkoxylated unsaturates, and preferably less than about 5 mole percent of polyoxyalkylene diols. The monoethers offer substantial advantages for fuel compositions, particularly reduced water affinity. By using deposit-control additives based on the monoethers, formulators can offer better fuels for cleaner engines.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

## POLYOXYALKYLENE MONOETHERS WITH REDUCED WATER AFFINITY

5

### FIELD OF THE INVENTION

The invention relates to polyoxyalkylene monoethers. In particular, the invention relates to polyoxyalkylene monoethers with reduced water affinity that have value as components of fuel additive detergent systems:

10

### BACKGROUND OF THE INVENTION

Polyoxyalkylene monoethers and their derivatives are well known and are widely used as components of fuel additive detergent systems to maintain the cleanliness of intake systems in internal combustion engines. Many traditional detergent systems have two components: (1) a polyoxyalkylene component, which acts as a carrier; and (2) a detergent. A wide variety of detergents are known, including carbamates, succinates, amine polyethers, and polyisobutylene amines (PIB amines). Examples of such two-component systems are those shown in U.S. Pat. Nos. 5,298,039 and 4,877,416. More recently, one-component detergent systems that incorporate a polyoxyalkylene moiety and a detergent function into a single polymer backbone have surfaced (see, for example, U.S. Pat. Nos. 5,427,591 and 5,600,025).

Polyoxyalkylene monoethers used as fuel additives must be oleophilic to be compatible with gasolines and the lipophilic detergents used to discourage or eliminate deposit formation. To achieve good solubility in and compatibility with fuels, polyoxyalkylene components are typically terminated with C<sub>4</sub>-C<sub>60</sub> (more preferably C<sub>9</sub>-C<sub>30</sub>) hydrocarbyl (alkyl, aryl, or aralkyl) groups as described, for example, in U.S. Pat. Nos. 5,298,039, 4,877,416, and 4,422,856. Even with the hydrocarbyl groups present, the polyoxyalkylene components can be hydrophilic enough to form emulsions on contact with water in the fuel, or to phase separate from other hydrocarbon components.

30

To enhance oil-solubility of polyoxyalkylene monoethers, formulators increase the oleophilic nature of the initiator alcohol (see, e.g., U.S. Pat. Nos. 5,298,039 and 5,600,025) or incorporate relatively hydrophobic oxyalkylene units such as those derived from C<sub>4</sub> epoxides (see, e.g., U.S. Pat. No. 5,004,478) or branched C<sub>11</sub>-C<sub>14</sub> epoxides (see, e.g., U.S. Pat. No. 4,274,837). Unfortunately, these modifications are often more costly than desirable.


Polyoxyalkylene monoethers normally contain relatively minor amounts of polyoxyalkylene diol impurities. These diol impurities result from base-catalyzed polymerization of alkylene oxides, e.g., propylene oxide, in the presence of water, which acts as a starter for the polymerization. The diols lack the hydrocarbyl moiety of the monoethers. Until now, these minor amounts of diol impurities were not believed to adversely affect the performance of polyoxyalkylene monoethers in fuels.

Polyoxyalkylene monoethers made with C<sub>3</sub> and higher alkylene oxides contain a second type of impurity: alkoxylated unsaturates. A side reaction complicates base-catalyzed polymerization of many alkylene oxides: some of the alkylene oxide isomerizes to an allylic alcohol and other unsaturates under the reaction conditions. For example, propylene oxide isomerizes to allyl alcohol under basic conditions. Reaction of the allylic alcohol with the alkylene oxide gives alkoxylated unsaturates. While these impurities are "monoethers," they lack a relatively hydrophobic end group. Until now, these alkoxylated unsaturates, usually propoxylated allyl alcohols, were not believed to adversely affect the performance of polyoxyalkylene monoethers in fuels.

#### SUMMARY OF THE INVENTION

The invention is an oleophilic polyoxyalkylene monoether. The monoether has the structure:

30



wherein A is an oxyalkylene group, Z is a hydrocarbyl residue selected from the group consisting of C<sub>4</sub>-C<sub>60</sub> alkyl, aryl, and aralkyl, and n, which is the average number of oxyalkylene groups, is within the range of about 2 to about 500. The monoether contains less than about 6 mole percent of  
5 alkoxyated unsaturates, and preferably less than about 5 mole percent of polyoxyalkylene diols.

We surprisingly found that polyoxyalkylene monoethers containing less than about 6 mole percent of alkoxyated unsaturates offer substantial advantages for fuels. In particular, the monoethers have reduced water  
10 affinity and a substantially reduced tendency to form emulsions with water present in lipophilic systems. These advantages of the monoethers suggest better fuel solubility. We also surprisingly found that reducing the content of polyoxyalkylene diol impurities in the monoethers to less than about 5 mole percent offers similar advantages. By using deposit-control  
15 additives based on polyoxyalkylene monoethers of the invention, fuel formulators can offer better solutions for cleaner engines.

#### DETAILED DESCRIPTION OF THE INVENTION

Oleophilic polyoxyalkylene monoethers of the invention have the  
20 general structure Z—(A)<sub>n</sub>—OH, in which A is an oxyalkylene group, Z is a hydrocarbyl residue, and n is the average number of oxyalkylene groups.

Suitable oxyalkylene groups (A) result from ring-opening polymerization of one or more epoxides, including, for example, propylene oxide, butene oxides, pentene oxides, and the like. Preferably, the  
25 polyoxyalkylene moiety of the monoether comprises recurring units derived from at least 50 mole percent of propylene oxide, up to about 49 mole percent of butene oxides, and not more than about 10 mole percent of ethylene oxide. Particularly preferred are polyoxyalkylene monoethers in which all of the oxyalkylene units are oxypropylene. The polyoxyalkylene  
30 moiety can include a random configuration of oxyalkylene units, or it can be

a block copolymer.

The average number of oxyalkylene groups in the monoether, which is represented by "n" in the formula, is within the range of about 2 to about 500. For preferred monoethers, n is within the range of about 5 to about 100. More preferred is the range from about 10 to about 30; most preferred is the range from about 10 to about 25.

The monoethers include a hydrocarbyl residue (Z). The hydrocarbyl residue is a  $C_4$ - $C_{60}$ , more preferably a  $C_9$ - $C_{30}$ , alkyl, aryl, or aralkyl group. The hydrocarbyl residue is generally derived from a monohydroxy compound (e.g., an alcohol or phenol), which is a starter for an epoxide polymerization to make the polyoxyalkylene monoether. Particularly preferred are monoethers that derive from phenols substituted with  $C_4$ - $C_{15}$  alkyl groups, e.g., nonylphenol, and monoethers that derive from  $C_{10}$ - $C_{20}$ , more preferably  $C_{12}$ - $C_{15}$ , aliphatic alcohols. Examples of generally suitable structures for the polyoxyalkylene monoether appear in U.S. Pat. Nos. 4,234,321, 4,288,612, and 5,600,025, the teachings of which are incorporated herein by reference. Suitable hydrocarbyl residues include "pinwheel" type oxyalkylated alkylphenols such as those described in U.S. Pat. No. 5,600,025.

Polyoxyalkylene monoethers are normally made by basic catalysis, and consequently, they include significant concentrations of alkoxylated unsaturates, typically propoxylated  $C_3$  unsaturates. Until now, these impurities were not believed to adversely affect the performance of polyoxyalkylene monoethers in fuels. We surprisingly found, however, that the concentration of alkoxylated unsaturates is important, and that polyoxyalkylene monoethers that contain less than about 6 mole percent of the alkoxylated unsaturates offer substantial advantages for fuels, including reduced water affinity and a reduced tendency to emulsify with water in lipophilic systems. More preferred polyoxyalkylene monoethers contain less than about 3 mole percent of alkoxylated unsaturates; most

preferred are monoethers having less than about 1.5 mole percent of alkoxyated unsaturates.

While there are several ways known in the art for making polyether compositions having very low concentrations of alkoxyated unsaturates (i.e., less than about 6 mole percent), a particularly valuable way is to make the polyoxyalkylene component using a double metal cyanide (DMC) catalyst. Suitable DMC catalysts, methods for their manufacture, and procedures for using them to catalyze epoxide polymerizations are described in U.S. Pat. Nos. 3,278,457, 3,941,849, 4,472,560, 5,158,922, 5,470,813, 5,482,908, the teachings of which are incorporated herein by reference. Particularly preferred are polyoxyalkylene monoethers prepared using substantially non-crystalline varieties of double metal cyanide catalysts, since those catalysts tend to give polymers with the lowest levels of alkoxyated unsaturates, typically less than about 3 mole percent, and often less than about 1.5 mole percent.

Preferred polyoxyalkylene monoethers also contain less than about 5 mole percent of polyoxyalkylene diols. Because the alcohol and phenol starters used to make polyoxyalkylene monoethers normally contain appreciable concentrations of water, base-catalyzed alkoxylation of the starter gives the desired monoether, but also gives a significant proportion of polyoxyalkylene diol resulting from epoxide polymerization with water as a starter. Until now, these diol impurities were not believed to adversely affect the performance of polyoxyalkylene monoethers in fuels. We surprisingly found, however, that the concentration of polyoxyalkylene diols is important, and that polyoxyalkylene monoethers that contain less than about 5 mole percent of the diols offer the advantages for fuels described earlier of using monoethers having a low content of alkoxyated unsaturates: reduced water affinity and a reduced tendency to emulsify with water in lipophilic systems. More preferred polyoxyalkylene monoethers contain less than about 2 mole percent of polyoxyalkylene diols.

To produce a polyoxyalkylene monoether having less than about 5 mole percent of polyoxyalkylene diols usually requires vacuum stripping of the starter molecule (alcohol or phenol derived from the hydrocarbyl moiety, Z) to reduce the water content of the starter. The stripping is usually performed at elevated temperature, preferably at a temperature within the range of about 60°C to about 200°C, more preferably from about 90°C to about 150°C. Purging the system with an inert gas such as nitrogen often helps to remove water. Azeotroping solvents (e.g., toluene, hexanes) can also be used to help strip out water. Before any epoxide is added to the starter and catalyst, the level of water in the starter is preferably less than about 5 mole percent.

As the results in Table 1 show, reduced water affinity results when the polyoxyalkylene monoethers contain low enough levels of diol and alkoxyated unsaturate impurities. When both diol and alkoxyated unsaturate contents are low, the tendency to form emulsions with water is relatively low. See Examples 1, 2, 5, and 7, in which the diol content is less than 5 mole percent, and the alkoxyated unsaturate content is less than 6 mole percent. Interfacial thickness, which is a measure of the monoether's tendency to form emulsions, is less than 5 mm in each case. In contrast, when the level of diol and/or alkoxyated unsaturate impurities is high (Comparative Examples 3, 4, and 6), the monoethers have a greater tendency to emulsify with water (interfacial thicknesses greater than 10 mm). The invention includes deposit-control additives based on the polyoxyalkylene monoethers. Two-component deposit-control additives of the invention comprise a detergent and the monoether. Suitable detergents are well-known in the art, and are described, for example, in U.S. Pat. Nos. 5,298,039 and 4,877,416, the teachings of which are incorporated herein by reference. Suitable detergents include, for example, carbamates, succinates, amine polyethers, polyisobutylene amines, and the like, and mixtures thereof. One-component deposit-control additives of



the invention incorporate a polyoxyalkylene moiety and a detergent function into a single polymer backbone. Examples of such one-component deposit-control additives appear, for example, in U.S. Pat. Nos. 5,427,591 and 5,600,025, the teachings of which are incorporated herein by reference.

5 The invention also includes fuel compositions made using the oleophilic polyoxyalkylene monoethers. The fuel compositions comprise a fuel and either a one-component or two-component deposit-control additive of the invention as described above. The fuel compositions may include other additives commonly known in the art, such as, for example, additional detergent additives, anti-knock agents; cetane enhancers, octane enhancers, and the like.

10 The following examples merely illustrate the invention. Those skilled in the art will recognize many variations that are within the spirit of the invention and scope of the claims.

#### EXAMPLE A

##### Preparation of a Polyoxypropylene Monoether from Nonylphenol

20 Nonylphenol (1006 g) is charged to a stainless-steel reactor. Zinc hexacyanocobaltate-tert-butyl alcohol complex (0.143 g, prepared as described in U.S. Pat. No. 5,482,908) is added, and the mixture is heated with stirring under vacuum at 130°C for 1 h to remove traces of water from the nonylphenol starter. Propylene oxide (4694 g) is introduced into the reactor over 6 hours. After the epoxide addition is complete, the mixture is heated at 130°C until no further pressure decrease occurs. The product is vacuum stripped and drained from the reactor.

#### EXAMPLE B

##### Preparation of a Polyoxyalkylene Monoether from a C<sub>12</sub>-C<sub>15</sub> Propoxylate

30 The procedure of Example A is generally followed, except that a

C<sub>12</sub>-C<sub>15</sub> fatty alcohol is used to initiate the polymerization. The amount of propylene oxide is adjusted to produce a monoether product having the desired number of oxypropylene (PO) units (see Table 1).

5

## EXAMPLE C

Measurement of Mole % Diols and Propoxylated C<sub>3</sub> Unsaturates

The mole % of polyoxyalkylene diols and propoxylated C<sub>3</sub> unsaturates reported in Table 1 are determined as follows. A polyoxyalkylene monoether sample is derivatized by reacting the hydroxyl groups in the sample with an excess of phthalic anhydride. The sample contains two kinds of "monols" (the desired polyoxyalkylene monoether and propoxylated C<sub>3</sub> unsaturates) in addition to polyoxyalkylene "diols." The hydroxyl groups in the sample are converted to phthalate half-esters, which have free -COOH groups. The relative amounts of diol and monols are then quantified by ion chromatography. Because the chromatography method does not distinguish between the two types of monols present, determination of the mole % of propoxylated C<sub>3</sub> unsaturates requires a second measurement. Polyol unsaturation, determined in the usual way by mercuric acetate titration, gives the mole % of monol due to the propoxylated C<sub>3</sub> unsaturates. Subtracting this value from the total mole % of monol as found by the chromatography method gives the mole % of polyoxyalkylene monoether.

15

20

## EXAMPLES 1-7

## 25 Emulsification Testing for Water Affinity of Polyoxyalkylene Monoethers

Generally, a modified version of ASTM method D-1094-96 is followed. Polyoxypropylene monoether samples (0.02 g) are combined with hexanes (3.6 g) in a screw-capped vial. The capped vial is swirled gently to completely dissolve the polyether. The cap is removed, and water (1.0 g) is added to the hexane solution. The vial is capped and shaken for

30

2 min. using a piston-like motion that traverses an arc of about 12 inches. The vial is shaken at 2-3 strokes per second for 2 min., and is then allowed to stand undisturbed for 5 min. A ruler is used to measure the height of the interfacial region (emulsified part) in mm after 5 min. and again after 30 min.

5

Table 1. Emulsification Test Results: Polyoxypropylene Monoethers


Ex. #	Mono-ether	# PO units	Diol (mole %)	C <sub>3</sub> olefin (mole %)	Purity (%)	5 min. IF thickness (mm)	30 min. IF thickness (mm)
1	A	24	< 0.5	0.4	> 99	5.6	4.0
2	B	18	< 0.5	0.5	> 99	4.8	4.0
C3	C	24	1.4	12.4	86	13	9.5
C4	D	17	< 0.5	6.8	93	16	13
5	E	18	2.4	5.5	92	< 3.2	2.4
C6	F	19	9.0	11	80	16	15
7	G	18	3.0	0.6	96	4.0	3.2

A, B = C<sub>12</sub>-C<sub>15</sub> alcohol-started; zinc hexacyanocobaltate-tert-butyl alcohol catalyst for propoxylation.  
 C, D = C<sub>12</sub>-C<sub>15</sub> alcohol-started; KOH catalyst for propoxylation.  
 E, F = Nonylphenol-started; KOH catalyst for propoxylation.  
 G = Nonylphenol-started; zinc hexacyanocobaltate-tert-butyl alcohol catalyst for propoxylation.  
 IF = interfacial

The preceding examples are meant only as illustrations; the following claims define the scope of the invention.

We claim:

1. An oleophilic polyoxyalkylene monoether of the structure:



wherein A is an oxyalkylene group, Z is a hydrocarbyl residue selected from the group consisting of C<sub>4</sub>-C<sub>60</sub> alkyl, aryl, and aralkyl, and n, which is the average number of oxyalkylene groups, is within the range of about 2 to about 500;

wherein the monoether contains less than about 5 mole percent of polyoxyalkylene diols and less than about 6 mole percent of alkoxyated unsaturates.

2. The monoether of claim 1 wherein A is oxypropylene.

3. The monoether of claim 1 wherein Z derives from nonylphenol.


4. The monoether of claim 1 wherein Z derives from a C<sub>12</sub>-C<sub>15</sub> aliphatic alcohol.

5. The monoether of claim 1 wherein Z is selected from the group consisting of C<sub>4</sub>-C<sub>30</sub> alkyl, aryl, and aralkyl.

6. The monoether of claim 1 wherein n has a value within the range of about 10 to about 30.

7. The monoether of claim 1 containing less than about 2 mole percent of polyoxyalkylene diols and less than about 3 mole percent of alkoxyated unsaturates.

8. An oleophilic polyoxyalkylene monoether of the structure:



wherein A is an oxyalkylene group, Z is a hydrocarbyl residue selected from the group consisting of C<sub>4</sub>-C<sub>60</sub> alkyl, aryl, and aralkyl, and n, which is the average number of oxyalkylene groups, is within the range of about 2 to about 500;

wherein the monoether contains less than about 5 mole percent of polyoxyalkylene diols.


9. The monoether of claim 8 wherein A is oxypropylene.

10. The monoether of claim 8 wherein Z is selected from the group consisting of C<sub>4</sub>-C<sub>30</sub> alkyl, aryl, and aralkyl.

11. The monoether of claim 8 wherein n has a value within the range of about 10 to about 30.

12. The monoether of claim 8 containing less than about 2 mole percent of polyoxyalkylene diols.

13. An oleophilic polyoxyalkylene monoether of the structure:



wherein A is an oxyalkylene group, Z is a hydrocarbyl residue selected from the group consisting of C<sub>4</sub>-C<sub>60</sub> alkyl, aryl, and aralkyl, and n, which is the average number of oxyalkylene groups, is within the range of about 2 to about 500;

wherein the monoether contains less than about 6 mole percent of alkoxyated unsaturates.


14. The monoether of claim 13 wherein A is oxypropylene.

15. The monoether of claim 13 wherein Z is selected from the group consisting of C<sub>4</sub>-C<sub>30</sub> alkyl, aryl, and aralkyl.

16. The monoether of claim 13 wherein n has a value within the range of about 10 to about 30.

17. The monoether of claim 13 containing less than about 3 mole percent of alkoxyated unsaturates.

18. An oleophilic polyoxypropylene monoether of the structure:



wherein A is an oxypropylene group, Z is a hydrocarbyl residue selected from the group consisting of C<sub>4</sub>-C<sub>60</sub> alkyl, aryl, and aralkyl, and n, which is the average number of oxypropylene groups, is within the range of about 10 to about 30;

wherein the monoether contains less than about 5 mole percent of polyoxypropylene diols and less than about 6 mole percent of propoxylated C<sub>3</sub> unsaturates.

19. The monoether of claim 18 containing less than about 2 mole percent of polyoxypropylene diols and less than about 3 mole percent of propoxylated C<sub>3</sub> unsaturates.

20. A one-component deposit-control additive that derives from the polyoxyalkylene monoether of claim 1.

21. A two-component deposit-control additive which comprises a detergent and the polyoxyalkylene monoether of claim 1.

22. A composition which comprises a fuel and the one-component deposit-control additive of claim 20.

23. A composition which comprises a fuel and the two-component deposit-control additive of claim 21.

24. A one-component deposit-control additive which derives from the polyoxyalkylene monoether of claim 13.

25. A two-component deposit-control additive which comprises a detergent and the polyoxyalkylene monoether of claim 13.

26. A composition which comprises a fuel and the one-component deposit-control additive of claim 24.

27. A composition which comprises a fuel and the two-component deposit-control additive of claim 25.

28. The monoether of claim 1 prepared using a double metal cyanide catalyst.

29. The monoether of claim 13 prepared using a double metal cyanide catalyst.

30. A method of reducing the water affinity of a fuel composition, said method comprising using as a fuel component the polyoxyalkylene monoether of claim 1.

31. A method for reducing the water affinity of a fuel composition, said method comprising using as a fuel component the polyoxyalkylene monoether of claim 13.



# INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 98/01640

**A. CLASSIFICATION OF SUBJECT MATTER**  
 IPC 6 C08G65/26 C10L1/18

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08G C10L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 962 237 A (LAYCOCK DAVID E) 9 October 1990 see claims 1,2,9 see column 2, line 29 - line 32 ----	13-17
X	EP 0 090 444 A (SHELL INT RESEARCH) 5 October 1983 see claims 1,15,16 see page 11, line 1 see page 1, line 11 ----	13-17, 24,29
X	US 3 941 849 A (HEROLD ROBERT JOHNSTON) 2 March 1976 cited in the application see claims 1,5 ----- -/-	13-17

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

30 June 1998

Date of mailing of the international search report

09/07/1998

Name and mailing address of the ISA  
 European Patent Office, P.B. 5818 Patentlaan 2  
 NL - 2280 HV Rijswijk  
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
 Fax: (+31-70) 340-3016

Authorized officer

O'Sullivan, T

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 98/01640

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 654 302 A (ARCO CHEM TECH) 24 May 1995 see claim 20 ---	1,13,18, 24
A	WO 94 29362 A (ICI PLC) 22 December 1994 see example 2 ---	1,13,18
A	EP 0 687 699 A (ARCO CHEM TECH) 20 December 1995 see claims 1,6-8 see page 5, line 13 - line 18 ---	1,20,21
A	US 4 573 488 A (CARVILLE DONNA B ET AL) 4 March 1986 see claim 1 see column 1, line 44 - line 46 see column 1, line 56 - line 58 -----	1,20,21

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 98/01640

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4962237 A	09-10-1990	US 4962281 A	09-10-1990
EP 0090444 A	05-10-1983	AU 551979 B	15-05-1986
		BR 8301675 A	13-12-1983
		CA 1226294 A	01-09-1987
		DE 3378690 A	19-01-1989
		JP 1772455 C	14-07-1993
		JP 4063013 B	08-10-1992
		JP 58185433 A	29-10-1983
		US 4477589 A	16-10-1984
US 3941849 A	02-03-1976	US 3829505 A	13-08-1974
EP 0654302 A	24-05-1995	US 5470813 A	28-11-1995
		AU 5228196 A	01-08-1996
		AU 7901894 A	01-06-1995
		BR 9404711 A	08-08-1995
		CA 2134596 A	24-05-1995
		CN 1107482 A	30-08-1995
		HU 71626 A	29-01-1996
		JP 7196778 A	01-08-1995
		US 5589431 A	31-12-1996
		US 5731407 A	24-03-1998
		ZA 9409079 A	02-05-1996
WO 9429362 A	22-12-1994	AU 676744 B	20-03-1997
		AU 6971494 A	03-01-1995
		CA 2162864 A	22-12-1994
		CN 1125455 A	26-06-1996
		EP 0703936 A	03-04-1996
		JP 8511046 T	19-11-1996
		US 5767324 A	16-06-1998
EP 0687699 A	20-12-1995	US 5426174 A	20-06-1995
		CA 2146477 A	11-12-1995
		JP 8157591 A	18-06-1996
US 4573488 A	04-03-1986	NONE	

**THIS PAGE BLANK (USPTO)**

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**

**THIS PAGE BLANK (USPTO)**